



Insert behavior

Objective

The metal insert should have no more than 3 corrosion points, none of which should be larger than 2 mm.

Principle

The insert is exposed to a sodium chloride solution in accordance with EN ISO 22568-1 §5.5 for seven days. The number of corrosion zones and the greatest length of each zone are then recorded.

Type: [Physical and mechanical test](#)

Standards: [EN ISO 20344 §5.11.2](#) / [EN ISO 20345 §6.2.1.4.2](#)

Product: [Footwear](#)

Criteria: [Mechanical risk](#) / [PEE](#)

Component: [Insert](#)

Last modified on 2025-05-28