Flex resistance of the upper On Bally Flexometer

Objective



This test reproduces the stresses to which the materials are subjected during flexing movements on the upper when walking. It is used to check for the appearance of defects such as cracking, splitting, etc.

Principle

The test consists of repeating a swinging flex motion after mounting a specimen taken from the shoe on a special machine commonly known as the Bally flexometer. The test can be performed dry and/or wet.
The result corresponds to the number of flexes taken to obtain deterioration of the material (crack, detachment, split, etc.).

Type: Physical and mechanical test
Standard: EN ISO 17694
Product: Footwear
Criteria: Mechanical resistance
Components: Leather upper / Textil upper

Last modified on 2025-03-28

CTC - 4, rue Hermann Frenkel - 69367 Lyon Cedex 07 - France - ctclyon@ctcgroupe.com - +33 (0)4 72 76 10 10