

Fastness of leather grain (Ball burst test)

Objective

During assembly (shoe or leather goods), the leather is subjected to stresses over a small surface, with the leather grain heavily stressed. This test is used to evaluate risks of deterioration (cracks or burst grain) during these operations.

Principle

The test consists in positioning the leather in a clamping system and subjecting it to a deformation force via a ball moving at constant speed. The sag is measured when deterioration appears. The result corresponds to the movement of the ball when the crack and grain burst occur, expressed in mm.

Type: Physical and mechanical test

Standard: EN ISO 3379

Product: Leather

Criteria: Mechanical resistance



Last modified on 2025-04-16